


| | |
|--|--|
| Office Address: | Manufacturing Site Address: |
| Plot No. 6, 2 nd Floor, Aparna Palm Gloves, Phase-IV, Kompally, Hyderabad, Telangana-500 100, India. Ph. No.: +91-7337770389. Web Site: www.siandcresins.com . | # 8 & 9B/30, Mirra Industrial Estate, IDA Phase-1, Patancheru, Sangareddy, Hyderabad-502 319, Telangana, India. Ph. No.: +91-9291517240. Email id.: business@siandcresins.com |

| Product Specifications | |
|---|---|
| Product Name: Fmoc-L-Alanine-Rinkamide AM Resin, Synonym: Fmoc-L-Ala-Rinkamide AM Resin | |
| Catalogue No.: SICA3-001 | CAS No.: N/A |
| Structure: |  |

| | |
|----------------------------------|----------------------------------|
| Appearance | Off-white to slight yellow beads |
| Bead size (Mesh) | 100 – 200 |
| Degree of cross-linking (% DVB) | 1 |
| Substitution (mmol/g) | 0.3 – 0.6 |
| Loss on drying (%) | ≤ 2.0 |
| Degree of swelling in DCM (ml/g) | 5.0 – 9.0 |
| Degree of swelling in DMF (ml/g) | 4.0 – 8.0 |
| Kaiser Test | Negative |
| Storage (°C) | 2 - 8 |