Office Address:	**Manufacturing Site Address:**
Plot No. 6, 2nd Floor, Aparna Palm Gloves, Phase-IV, Kompally, Hyderabad, Telangana-500 100, India. Ph. No.: +91-7337770389. Web Site: www.siandcresins.com.	# 8 & 9B/30, Mirra Industrial Estate, IDA Phase-1, Patancheru, Sangareddy, Hyderabad-502 319, Telangana, India. Ph. No.: +91-9291517240. Email id.: business@siandcresins.com

Product Specifications	
Product Name: Fmoc-O-butyl-L-Aspartic acid-Rinkamide MBHA Resin, Synonym: Fmoc-L-Asp(OtBu)-Rinkamide MBHA Resin	
Catalogue No.: SICD5-001	CAS No.: N/A
Structure:	

Appearance	Pale or Light Yellow to brown Beads
Bead size (Mesh)	100 – 200
Degree of cross-linking (% DVB)	1
Substitution (mmol/g)	0.3 – 0.6
Loss on drying (%)	≤ 2.0
Degree of swelling in DCM (ml/g)	4.0 – 8.0
Degree of swelling in DMF (ml/g)	4.0 – 8.0
Kaiser Test	Negative
Storage (°C)	2 - 8