


<b>Office Address:</b>	<b>Manufacturing Site Address:</b>
Plot No. 6, 2 <sup>nd</sup> Floor, Aparna Palm Gloves, Phase-IV, Kompally, Hyderabad, Telangana-500 100, India. Ph. No.: +91-7337770389. Web Site: <a href="http://www.siandcresins.com">www.siandcresins.com</a> .	# 8 & 9B/30, Mirra Industrial Estate, IDA Phase-1, Patancheru, Sangareddy, Hyderabad-502 319, Telangana, India. Ph. No.: +91-9291517240. Email id.: <a href="mailto:business@siandcresins.com">business@siandcresins.com</a>

<b>Product Specifications</b>	
Product Name: N-Fmoc-O-butyl-L-glutamic acid-Rinkamide MBHA Resin, Synonym: Fmoc-L-Glu(OtBu)-Rinkamide MBHA Resin	
Catalogue No.: SICE5-001	CAS No.: N/A
Structure:	

*Solid Supports, Scavengers & Stationary Phases*

Appearance	Pale or Light Yellow to brown Beads
Bead size (Mesh)	100 – 200
Degree of cross-linking (% DVB)	1
Substitution (mmol/g)	0.3 – 0.6
Loss on drying (%)	≤ 2.0
Degree of swelling in DCM (ml/g)	4.0 – 8.0
Degree of swelling in DMF (ml/g)	4.0 – 8.0
Kaiser Test	Negative
Storage (°C)	2 - 8