


| | |
|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Office Address: | Manufacturing Site Address: |
| Plot No. 6, 2 nd Floor, Aparna Palm Gloves, Phase-IV, Kompally, Hyderabad, Telangana-500 100, India. Ph. No.: +91-7337770389. Web Site: www.siandcresins.com . | # 8 & 9B/30, Mirra Industrial Estate, IDA Phase-1, Patancheru, Sangareddy, Hyderabad-502 319, Telangana, India. Ph. No.: +91-9291517240. Email id.: business@siandcresins.com |

| Product Specifications | |
|------------------------------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------|
| Product Name: N-Fmoc-N-Boc-L-ornithine-Rinkamide MBHA Resin, Synonym: Fmoc-L-Orn(Boc)-Rinkamide MBHA Resin | |
| Catalogue No.: SICO5-001 | CAS No.: N/A |
| Structure: |  |

Solid Supports, Scavengers & Stationary Phases

| | |
|----------------------------------|-------------------------------------|
| Appearance | Pale or Light Yellow to brown Beads |
| Bead size (Mesh) | 100 – 200 |
| Degree of cross-linking (% DVB) | 1 |
| Substitution (mmol/g) | 0.3 – 0.6 |
| Loss on drying (%) | ≤ 2.0 |
| Degree of swelling in DCM (ml/g) | 4.0 – 8.0 |
| Degree of swelling in DMF (ml/g) | 4.0 – 8.0 |
| Kaiser Test | Negative |
| Storage (°C) | 2 - 8 |