


| | |
|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Office Address: | Manufacturing Site Address: |
| Plot No. 6, 2 nd Floor, Aparna Palm Gloves, Phase-IV, Kompally, Hyderabad, Telangana-500 100, India. Ph. No.: +91-7337770389. Web Site: www.siandcresins.com . | # 8 & 9B/30, Mirra Industrial Estate, IDA Phase-1, Patancheru, Sangareddy, Hyderabad-502 319, Telangana, India. Ph. No.: +91-9291517240. Email id.: business@siandcresins.com |

| Product Specifications | |
|-----------------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------|
| Product Name: Fmoc-o-trityl-L-Serine-2-Chlorotrityl Resin, Synonym: FmocL-Ser(Trt)-2-CT Resin | |
| Catalogue No.: SICS6-001 | CAS No.: N/A |
| Structure: |  |

| | |
|----------------------------------|-------------------------------------|
| Appearance | Pale or Light yellow to brown beads |
| Bead size (Mesh) | 100 - 200 |
| Degree of cross-linking (% DVB) | 1 |
| Substitution (mmol/g) | 0.3 - 0.8 |
| Loss on drying (%) | ≤ 2.0 |
| Degree of swelling in DCM (ml/g) | 4.0 - 8.0 |
| Degree of swelling in DMF (ml/g) | 3.0 - 8.0 |
| Storage (°C) | 2 - 8 |