


Office Address:	Manufacturing Site Address:
Plot No. 6, 2 nd Floor, Aparna Palm Gloves, Phase-IV, Kompally, Hyderabad, Telangana-500 100, India. Ph. No.: +91-7337770389. Web Site: www.siandcresins.com .	# 8 & 9B/30, Mirra Industrial Estate, IDA Phase-1, Patancheru, Sangareddy, Hyderabad-502 319, Telangana, India. Ph. No.: +91-9291517240. Email id.: business@siandcresins.com

Product Specifications	
Product Name: Fmoc-o-tert-butyl-L-tyrosine -2-Chlorotrityl Resin Synonym: Fmoc-L-Tyr(tBu)-2-CT Resin	
Catalogue No.: SICY6-001	CAS No.: N/A
Structure:	

Appearance	Pale or Light yellow to brown beads
Bead size (Mesh)	100 - 200
Degree of cross-linking (% DVB)	1
Substitution (mmol/g)	0.3 – 0.8
Loss on drying (%)	≤ 2.0
Degree of swelling in DCM (ml/g)	4.0 - 8.0
Degree of swelling in DMF (ml/g)	3.0 - 8.0
Storage (°C)	2 - 8